



S. R. Industries

STAR ARC ER330

ER330 is used to weld cast and wrought material of similar chemical composition. The weld metal provides excellent scale and heat resistance up to 1800°F. ER330 is a fully austenitic alloy therefore heat input is necessary. High sulfur environments may adversely affect temperature performance.

AWS Specification : AWS A5.9/A5.9M:2006

<i>AWS Classification</i>	ER330
<i>Welding Current</i>	DCEP
Typical Wire Chemistry	
<i>C</i>	0.18 - 0.25
<i>Cr</i>	15.0 - 17.0
<i>Ni</i>	34.0 - 37.0
<i>Mo</i>	0.75
<i>Mn</i>	1.0 - 2.5
<i>Si</i>	0.30 - 0.65
<i>P</i>	0.03
<i>S</i>	0.03
<i>Cu</i>	0.75
Typical Mechanical Properties (As Welded)	
<i>Yield Strength, ksi</i>	56
<i>Tensile Strength, ksi</i>	84
<i>Elongation%, min</i>	29
<i>Welding Positions</i>	F,V,OH,H
Available Diameters MIG with Operating Range in Amps	

Address : C-617, DSIIDC, Narela, Delhi-110040 India

Tel : 011 47506585 **Mobile :** + 91 9911166585

E.Mail : srindus@yahoo.com

Website : www.stararc.in



S. R. Industries

<i>.023"</i>	<i>35 - 70</i>
<i>.030"</i>	<i>50 - 100</i>
<i>.035"</i>	<i>160 - 210</i>
<i>.045"</i>	<i>180 - 250</i>
<i>Available Diameters TIG with Operating Range in Amps</i>	
<i>.035"</i>	<i>60 - 90</i>
<i>.045"</i>	<i>80 - 110</i>
<i>1/16"</i>	<i>90 - 130</i>
<i>3/32"</i>	<i>120 - 175</i>
<i>1/8"</i>	<i>150 - 220</i>
<i>5/32"</i>	<i>170 - 350</i>

Address : C-617, DSIIDC, Narela, Delhi-110040 India
Tel : 011 47506585 Mobile : + 91 9911166585
E.Mail : srindus@yahoo.com
Website : www.stararc.in